



UN33-12HX (12V35Ah/10hr)

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and thus immobilized.

Should the battery be accidentally overcharged producing hydrogen and oxygen, Special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

General Feature


- Absorbent Glass Mat(AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.

Performance Characteristics

Capacity 77°F(25°C)	20 hour rate (1.85A、10.8V)	37Ah
	10 hour rate (3.5A、10.8V)	35Ah
	5 hour rate (5.9A、10.5V)	29.5Ah
	1 hour rate (25.8A、9.6V)	25.8Ah
Internal Resistance	Full charged Battery 77°F(25°C):7mΩ	
Capacity affected by Temperature (10 hour rate)	104° F(40°C)	102%
	77° F(25°C)	100%
	32° F(10°C)	85%
	5° F(-15°C)	65%
Self-Discharge 68°F(20°C)	Capacity after 3 month storage	90%
	Capacity after 6 month storage	80%
	Capacity after 12month storage	60%
Max. discharge current 77°F(25°C): 330A(5S)		
Charge (Constant Voltage)	Float: 13.6~13.8 V/77° F(25°C)	
	Cycle:14.4~14.7 V/77°F(25°C) Max. Current: 8.3A	

SPECIFICATION

Nominal voltage 12V
 Number of cell 6
 Length(mm/inch) 195/7.68
 Width(mm/inch) 130/5.12
 Height(mm/inch) 155/6.10
 Total Height(mm/inch) 168/6.61
 Approx. Weight(kg/lbs) 10.6/23.4











Discharge Constant Current (Amperes at 77° F25°C)

End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	20h
1.60V		96.3	71.5	45.5	25.8	10.7	6.65	3.70	1.95
1.65V		93.6	68.8	43.4	25.1	10.5	6.45	3.70	1.95
1.70V		90.0	67.5	41.4	24.3	10.3	6.20	3.65	1.90
1.75V		86.9	65.7	39.3	23.5	10.1	5.95	3.60	1.90
1.80V		83.7	63.5	37.3	22.5	9.90	5.70	3.50	1.85

Discharge Constant Power (watts at 77° F25°C)

End Point Volts/Cell	5min	10min	15min	30min	45min	1h	2h	3h	5h
1.60V		179	160	95.5	65.8	54.0	29.5	20.6	13.4
1.65V		171	153	92.7	63.9	53.0	28.8	20.2	13.1
1.70V		163	146	89.7	61.9	51.8	28.1	19.7	12.8
1.75V		157	139	86.7	59.9	50.6	27.4	19.2	12.5
1.80V		151	131	83.5	57.7	49.3	26.7	18.6	12.2

(Note)The above characteristics data are average values obtained Within three charge/discharge cycles not the minimum values.



OREMA POWER CO., LTD
 Add: Datang Industry Park Xinfeng Ganzhou City, Jiangxi Province, China
 TEL: +86-0797-2299669 +86-0797- 2299553
 FAX: +86-0797-2299553

www.oremabattery.com